



WALMASTA LITE



Product Attributes



Economical

Resistant
to Chalking
& Fading



Prevent Fungi
& Algae

**Green Pro
Certified**
Validates our
effort in
striving towards
cleaner, more
sustainable future.



Product Description

Walmasta Lite is a modified acrylic emulsion based exterior paint suitable for moderate to dry climate. It is an economically priced paint with a matt finish. The paint is resistant to chalking, flaking, fading as well as prevents the growth of fungus and algae common to cement paint.

Recommended Use

Sand/cement plaster, asbestos and concrete surfaces.

Note: Not recommended on lime wash.

Colour Range



Over 2,000 shades

Finish



Matt

Toxicity



VOC <50 gm/lit
No added Lead, Arsenic,
Chromium (VI) and Mercury

Coverage



Approx. 50 - 60 sq.ft/ lt/2 coats, under
ideal test conditions.

(Actual coverage may vary depending upon
surface conditions, preparation and type of shade)

Drying Time



SD: 30 minutes (depending on
weather conditions)

HD: 4 - 6 hours

Dilution



50 - 60% by volume with water

Recommended Thinner



Potable water

Application Method



Brush/ Roller/ Spray

Over Coating Interval



4 - 6 hours



WALMASTA LITE



Packs



1 Ltr



4 Ltr



Fire Hazard Class
Not flammable



Pot Life of Thinned Material
Use within 24 hours

Surface Preparation

For New Masonry surfaces



The surface should be allowed to cure completely.
Apply one coat of Illusion Sealer to avoid salt petering.

For Previously Painted Surfaces



Ensure the surface is free from all loose paints, dust particles, chalk, grease, fungus and algae. Sand the surface with Emery Paper No. 80 and wipe clean or scrub it clean by wire brushing.



Cracks, holes, dents or damp areas should be repaired properly before painting.



If required, treat the surface with Bio wash solution, wash it next day with potable water, and leave the surface to dry completely.

Priming:



Apply 1- 2 coats of WC Seal-O-Prime or WC Exterior Primer.

Directions for Application

Dilute the paint as per the recommended dilution ratio. Apply 2- 3 coats of WalmastaLite topcoat paint with 4 – 6 hours of interval.

PRECAUTIONS

- Stir well and strain the diluted paint before use
- Do not over dilute or over extend brush
- Do not apply paint on high alkaline surface (pH of wall should be below 12)
- Do not apply paint on wet surface (moisture content of wall should be below 12%)
- Do not apply paint on chalking or flaking surface or where the surface is infected with fungus and algae
- Do not apply paint if the ambient temperature is less than or expected to fall below 10° C
- Use only Berger Paints machine colourants to tint shades
- Allow sufficient time for each coat to dry before next coat application
- Primer or one coat of paint should not be left exposed. Ensure complete application of process

Version No: BPP1/08/2019. Please note that this data sheet supersedes all previous versions.

BERGER PAINTS INDIA LIMITED

Berger House, 129 Park Street, Kolkata 700 017 | **CONSUMER RELATIONS MANAGER** Ph: 1800-103-6030
Fax: 91-33-2249-9729/9009 | SMS BERGER to 56767 | Email: consumerfeedback@bergerindia.com | www.bergerpaints.com