

HS ShaliTex Sealing Compound

Bitumen Based Sealing Compound



Description

Home Shield ShaliTex Sealing Compound is bitumen-based sealant for concrete joints resistant to high temperature variations providing waterproof sealing for all type of horizontal joints. It is conforming to IS 1834 – 1984, Grade A specification.

Characteristics

Colour	Black	Theoretical Coverage, 100 meters of running joint of 25 mm depth, kg *	
Aviation Fuel / Kerosene Resistance Test, change in Penetration after 7 days immersion in Aviation fuel / kerosene, at 25 °C, 100 g./ 0.1 mm / 5 sec., max.	Not Applicable	<ul style="list-style-type: none">• 12 mm• 18 mm• 25 mm	<div>36</div> <div>54</div> <div>75</div>
		Pour Point, °C, Max	180
		Softening point °C, Min	85
Flow test, %, max.	5	Penetration, 25 °C, 0.1 mm, 5 sec.	15 - 50
Change in mass, %, max	Not Applicable	Extensibility, mm, min	6

* Depending upon surface condition.

Application

- Runway Joints
- Joints in garages, filling stations and other places of construction joints like in warehouse floors and secondary containment of walls and floors of artificial water ponds.
- Bridge / road joints.

Advantages

- Ability to withstand expansion without cracking
- Good adhesion to concrete / other surface.
- Low susceptibility to flow during hot weather condition.
- Resistant to sunlight / rain and cyclic temperature changes.
- Anti-corrosive and prevents root growth.
- Resistant to ingress of foreign substance.

Application Methodology

- Remove dust, flakes, oil, grease or other foreign particles by jet or dry air and clean the surface to make it smooth before applying **Home Shield ShaliTex Sealing Compound**.
- Spray or brush, on the area where **Home Shield ShaliTex Sealing Compound** is to be applied, Home Shield ShaliTex Primer evenly throughout the joints and allow it to dry completely. 24 hours is enough to dry the primer during normal weather condition.
- Cover the joint by plastic film if rain is expected after primer application.
- Cut **Home Shield ShaliTex Sealing Compound** drum and heat it to 180 – 210 °C while slowly stirring the material for uniformity. A 20 kg drum will take 2-3 hr at 190 – 200 °C for complete melting using hand stirrer. Do not overheat as this may cause frothing. If for any reason bubble appears during melting, keep the temperature around 180 °C for a longer time with slow manual stirring till the bubble disappears.
- Upon primer drying completely, pour molten **Home Shield ShaliTex Sealing Compound** from one side of the joint allowing it to travel through the joint as much as practicable. While pouring, ensure that temperature of material is in the range of 190 - 200 °C.

- During the pouring process, to avoid spillage, place wooden boards on both sides of joint and pour from can with extended spout.

Health & Safety.

- **Home Shield ShaliTex Sealing Compound** is inflammable.
- Use goggles, gumboots, nose covers and hand gloves during application
- Clean hands with warm soap water after application

Packing

Available in 20 kg and 200 kg drum.

Storage

Keep in cool and dry place, under shed, away from heat.

DISCLAIMER

The information contained within this Data Sheet is based on information believed to be reliable at the time of its preparation. The Company will not be liable for loss or damage howsoever caused including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

BERGER PAINTS INDIA LIMITED

Berger House. 129, Park Street, Kolkata : 700 017

Phone : 91-33-2229-9724-28 / 6005-06, Fax : 91-33-2227-7288, 2249-9009/9729

e-mail : consumerfeedback@bergerindia.com ; Website : www.bergerpaints.com